

PAPER • OPEN ACCESS

Observation of an anomalous Hall effect in single-crystal Mn_3Pt

To cite this article: Belén E Zuniga-Cespedes *et al* 2023 *New J. Phys.* **25** 023029

View the [article online](#) for updates and enhancements.

You may also like

- [Search for heavy Majorana neutrinos at future lepton colliders](#)
Peng-Cheng Lu, Zong-Guo Si, zhe wang et al.
- [Growth Mechanisms of hBN Crystalline Nanostructures with RF Sputtering Deposition: Challenges, Opportunities, and Future Perspectives](#)
Duc-Quang HOANG, Ngoc-Hai VU, Qui T. NGUYEN et al.
- [Strong perpendicular anisotropic ferromagnet \$\text{Fe}_3\text{GeTe}_2\$ /graphene van der Waals heterostructure](#)
Bing Zhao, Bogdan Karpiak, Anamul Md Hoque et al.



PAPER

Observation of an anomalous Hall effect in single-crystal Mn₃PtBelén E Zuniga-Cespedes¹ , Kaustuv Manna^{1,2}, Hilary M L Noad¹, Po-Ya Yang¹ , Michael Nicklas¹ ,
Claudia Felser¹, Andrew P Mackenzie^{1,3} and Clifford W Hicks^{1,4,*} ¹ Max Planck Institute for Chemical Physics of Solids, D-01187 Dresden, Germany² Department of Physics, Indian Institute of Technology Delhi, Hauz Khas, New Delhi 110016, India³ Scottish Universities Physics Alliance (SUPA), School of Physics and Astronomy, University of St. Andrews, St. Andrews KY16 9SS, United Kingdom⁴ School of Physics and Astronomy, University of Birmingham, Birmingham B15 2TT, United Kingdom

* Author to whom any correspondence should be addressed.

E-mail: c.hicks.1@bham.ac.uk**Keywords:** anomalous Hall effect, antiferromagnetism, noncollinear antiferromagnet, uniaxial pressure, Berry phase, Mn₃X

RECEIVED

12 September 2022

ACCEPTED FOR PUBLICATION

15 February 2023

PUBLISHED

24 February 2023

Original Content from
this work may be used
under the terms of the
[Creative Commons
Attribution 4.0 licence](https://creativecommons.org/licenses/by/4.0/).

Any further distribution
of this work must
maintain attribution to
the author(s) and the title
of the work, journal
citation and DOI.


**Abstract**

The Mn₃X family of compounds was the first in which a large anomalous Hall effect (AHE) was predicted to arise from a purely antiferromagnetic structure, due to the Berry curvature in momentum space. Nearly simultaneously with this prediction, a large AHE was observed experimentally in one of the hexagonal members of this family, Mn₃Sn. Aligning antiferromagnetic domains, a necessary step for observation of the AHE, is more challenging for the cubic members of the Mn₃X family, due to a combination of smaller spontaneous ferromagnetic moments and much stronger magnetic anisotropy. Here, we use a combination of uniaxial stress and applied magnetic field to align domains of bulk single-crystal Mn₃Pt, and demonstrate for the first time a substantial AHE in a bulk sample of a cubic member of the Mn₃X family. The AHE remains locked in with essentially no quantitative variation when the stress is ramped back to zero, which shows that it is not a consequence of any stress-induced ferromagnetic moment.

1. Introduction

The anomalous Hall effect (AHE) was long thought to be a direct consequence of the magnetisation M generated by ferromagnets [1]. However, in studies of the ferromagnet SrRuO₃ the anomalous Hall conductivity σ_{xy} was found to have a nonmonotonic dependence on M [2], and instead was found to be explainable as an integral of the spin Berry curvature in momentum space, following the proposal of Karplus and Luttinger [3]. This Berry phase mechanism is now understood to be the dominant mechanism for the intrinsic AHE [4]. One feature of this mechanism is that even antiferromagnets can generate a large AHE, as predicted, for example, for antiferromagnetism on a distorted fcc lattice [5], and observed experimentally in Pr₂Ir₂O₇ [6]. A large AHE is also predicted for the Mn₃X family of compounds [7, 8], which are antiferromagnetic. It has been demonstrated experimentally in bulk, single-crystal Mn₃Sn [9, 10], Mn₃Ge [11, 12], and Mn₃Ga [13]. A large, antiferromagnetically-induced AHE is a potentially valuable discovery for memory applications [14, 15].

These latter three compounds are all hexagonal. Other members of the Mn₃X family—Mn₃Pt, Mn₃Ir, and Mn₃Rh—are cubic. The cubic compounds are also expected to have large AHEs, but so far this has not been demonstrated in bulk single crystals. To observe the AHE in these compounds the magnetic structure must be trained, meaning that a subset of the possible antiferromagnetic domains must be selected, so that the AHE generated by individual domains does not cancel. It is easier to do so for the hexagonal compounds because they have an inverse-triangular spin configuration [16], within which the spins do not point in crystallographically equivalent directions. One consequence is that spin canting results in a net ferromagnetic moment, $3 m\mu_B/\text{Mn}$ in Mn₃Sn and $7 m\mu_B/\text{Mn}$ in Mn₃Ge, upon which applied magnetic field can act to select domains. Another is that the coercive field for domain re-orientation is low. The cubic compounds, on the other hand, have a triangular spin configuration in which the spins do point in



equivalent directions. Therefore, the magnetic anisotropy is 2–3 orders of magnitude higher than for the hexagonal compounds [17–20], a property that has made one member of this family, Mn_3Ir , technologically important as an exchange-bias layer [21–24]. The room-temperature magnetic structure of Mn_3Pt is shown in figure 1. The spins lie essentially within $\{111\}$ planes, within which the Mn atoms are arranged in a kagomé lattice. Cubic anisotropy is expected to introduce a slight rotation of the spins out of the plane [17, 25], resulting in a small net ferromagnetic moment.

A polarisable AHE has been observed in thin films of Mn_3Pt [26, 27], Mn_3Ir [28], and also Mn_3NiN [29], which is also cubic. The polarisability of thin films may be a consequence of the combination of epitaxial strain and piezomagnetism: under tetragonal lattice distortion, the spin directions become inequivalent, potentially causing spin canting and inducing a net ferromagnetic moment on which the field can act. Stress-driven spin canting has been observed for Mn_3Sn [30]. For thin films of Mn_3Pt and Mn_3Ir , the observed AHE was of the same order as theoretical predictions developed for bulk lattices [31]. However, observations might be substantially affected by interface effects and disorder, and for this reason it is important to observe the AHE in bulk single crystals.

Here, we report a large, hysteretic AHE in bulk single-crystal Mn_3Pt , using a combination of applied field and uniaxial stress to train the magnetic structure. We study Mn_3Pt rather than Mn_3Ir because the ductile nature of Mn_3Ir makes it difficult to apply uniaxial stress. The AHE appears as a stress-induced field hysteresis in the Hall effect. The AHE remains locked in when the stress is released, which shows that stress-induced magnetism is not itself the source of the AHE, in agreement with the expectation that it is the antiferromagnetic structure that generates the AHE.

2. Methods

Single crystals of $\text{L}1_2\text{-Mn}_3\text{Pt}$ were grown by the Bridgeman–Stockbarger method [32]. All samples studied here were cut from the same original crystal. Resistivity data from two samples are shown in figure 2. The resistivity at 300 K is $65 \pm 3 \mu\Omega\text{-cm}$, far smaller than the $175 \mu\Omega\text{-cm}$ measured for the epitaxial films of [26].

Stress was applied using a piezoelectric-based uniaxial stress cell that incorporates sensors of both the force and displacement applied to the sample [33]. To allow *in situ* calibration of the zero-stress point, samples were mounted onto carriers that allowed application of compressive but not tensile stress. Three different, though conceptually equivalent, designs were used; one is shown in figure 3(a). It comprises two parts, and force is applied to the sample when they are brought together.

Samples 1, 2, and 3 had a longitudinal configuration: compression along [001] and $\mathbf{H} \parallel [001]$. Qualitatively, this configuration matches that of the thin film study of [26], in which the epitaxial strain yielded $a > c$, where a is the lattice constant along [100] and [010]. This configuration obliges us to adopt a non-optimal contact configuration for measurement of the Hall resistivity: as shown in figures 3(b)–(d), current must be applied across the sample width. In a conventional configuration, the Hall voltage is:

$$V_y = \rho_{xy} I_x / t, \quad (1)$$

t is the sample thickness, perpendicular to the current direction, and in this configuration it is unclear what value is appropriate. $\rho_{xy} = R_H B + \rho_{\text{AHE}} + \rho_{\text{offset}}$, where R_H is the Hall coefficient, ρ_{AHE} the anomalous Hall resistivity, and ρ_{offset} is an offset due to misalignment of contacts. For samples 1–3, we applied equation (1) to




Figure 2. Temperature dependence of the resistivity of two samples of Mn_3Pt , at zero stress. The black lines are third-order polynomial fits, used later to calculate the Hall conductivity. The error bars indicate systematic uncertainty due to error in the placement of contacts.




Figure 3. Experimental setup. (a) Illustration of the sample carrier used for samples 1 and 4. The carrier is mounted onto a piezoelectric-driven cell that controls the distance between the pairs of anchor points. (b) Photograph of sample 1. (c) Schematic of the configuration for samples 1 and 3. The sample is held with epoxy between surfaces of the sample carrier, such that force is applied through the end faces of the sample. (d) Schematic of the configuration for sample 2. The ends of the sample are inserted into guides and secured with epoxy, such that force is applied to the sample dominantly through the side faces. The mounting epoxy for all samples was Stycast 2850FT, cured at 65°C for 180 minutes. (e) Applied force versus applied displacement for sample 4 at 100 K. The point labelled ‘carrier contact point’ is where the two parts of the carrier come into contact. The onset of plastic deformation is also indicated. The stress scale, on the right, is the stress applied to the sample.

obtain an effective thickness t_{eff} , so that R_{H} at zero stress would match that measured in sample 4, which had a conventional Hall bar configuration. This t_{eff} was then used to obtain the stress-driven changes in ρ_{xy} . Due to uncertainty in the true contact configuration, it is unlikely that more sophisticated analysis would yield better accuracy.

Sample 4 had a transverse configuration, with stress along $[100]$ and $\mathbf{H} \parallel [001]$, allowing a conventional contact configuration. A normal Hall coefficient of $R_{\text{H}} = -0.057 \mu\Omega\cdot\text{cm}/\text{T}$ was observed at 298 K. For comparison, R_{H} of a 20 nm-thick film of Mn_3Pt in [26] was $-0.044 \mu\Omega\cdot\text{cm}/\text{T}$ at 365 K.

All stress values quoted in this paper are based on a room-temperature calibration of the force sensor of the stress cell, and are accurate to within 10%. The flexures of the sample carriers constitute springs placed in parallel with the samples; their total spring constant is $0.044 \text{ N } \mu\text{m}^{-1}$ for the carrier illustrated in figure 3(a), and $0.023 \text{ N } \mu\text{m}^{-1}$ and $0.020 \text{ N } \mu\text{m}^{-1}$ for the other two designs. These spring constants are at most 5% of the spring constant of the sample system (see table 1), meaning that at least 95% of the applied force went into the sample rather than the carrier flexures.

Force-displacement data for sample 4 are shown in figure 3(e). There are two prominent features. One is the point where the two parts of the carrier come into contact, allowing force to be transmitted to the sample. Another is plastic deformation: the force-displacement relation transitioned to a shallower slope when the stress in this sample became larger than -0.18 GPa . (negative values denote compression.) As

Table 1. Key sample parameters. k is the spring constant of the sample system, which is the sample itself in series with the mounting epoxy, and in parallel with the flexures of the sample carrier. σ_{plastic} is the stress at which plastic deformation onset. Mount style A refers to a configuration like in figure 1(c), where force is applied dominantly through the sample's end faces, and B to a configuration like figure 1(d), where the sample ends are deeply embedded in epoxy such that force is applied mostly through the side faces. For all samples, the field axis is the [001] direction.

Sample #	Cross-section (mm ²)	Stress axis	k (N μm^{-1})	σ_{plastic}	Mount style
1	0.18 \times 0.18	[001]	1.09	−0.19 GPa at 300 K	A
2	0.40 \times 0.09	[001]	1.09	−0.20 GPa at 300 K	B
3	0.20 \times 0.20	[001]	1.20	−0.20 GPa at 100 K	A
4	0.30 \times 0.14	[100]	0.97	−0.18 GPa at 100 K	B

shown in table 1, plastic deformation began at a similar stress for all samples where it was observed, even at very different temperatures, and even for different mounting configurations (e.g.: figures 3(c) and (d)) in which the stress field within the epoxy that holds the sample would have differed. We interpret this consistency, and the fact that with the same mounting epoxy far higher stresses have been achieved in other materials [33], as showing that the plastic deformation occurred in the sample rather than the mounting epoxy. Evidently, the elastic limit of Mn₃Pt is much lower than that of Mn₃Sn, where elastic stresses larger than 1 GPa could be applied at temperatures near room temperature [34]. The experiment here was a constant battle with plastic deformation. We only report data taken in the elastic regime. Within the elastic limit and the maximum field in our measurement system, 12 T, we obtained clear magnetic hysteresis, but not complete polarisation of the domains.

3. Results

We begin with magnetometry measurements on unstressed samples, to investigate possible spontaneous ferromagnetism. As noted in the Introduction, the cubic symmetry of the lattice competes with nearest-neighbour antiferromagnetic interaction, and is expected to cause a small spin rotation out of the plane [17, 25]. For the domain illustrated in figure 1(a), the resulting net moment would point along the [111] or $[\bar{1}\bar{1}\bar{1}]$ direction. In Mn₃Ir, a net moment of 7 m μ_{B} /Mn has been predicted [7].



Mn₃Pt does not transition directly into the structure illustrated in figure 1(a), but rather passes through an intermediate phase between $T_{\text{I}} \approx 400$ K and $T_{\text{N}} \approx 475$ K with a collinear spin structure [35–37]. Data for $\mathbf{H} \parallel [111]$ are shown in figures 4(a), (c) and (d), and for $\mathbf{H} \parallel [100]$ in figures 4(b), (e) and (f). The samples were thermally cycled to 600 K, well above T_{N} , and cooled in either 0 or 7 T. For both samples, a net polarisation of 0.3–0.4 m μ_{B} /Mn is visible below T_{I} . This is a small net moment, and because it may include contributions from polarisation of spins in the vicinity of defects and magnetic domain walls, it should be understood as an upper limit on the intrinsic net moment.


We now discuss measurements of the Hall effect. ρ_{xy} data from sample 1 are shown in figure 5(a).

At zero stress (the blue curve), the field dependence of ρ_{xy} is dominated by the normal Hall effect. There is resolvable hysteresis, but it is small. Under an applied stress of −0.14 GPa (thick red and black curves), the hysteresis became much larger. When the stress was released after application of a field of +12 T at −0.14 GPa, the hysteresis loop closed up again, showing that the enhanced hysteresis was not a product of any non-elastic deformation. However, the new curve (the thin red curve) was offset from the original blue curve. Similarly, the zero-stress data recorded after application of −12 T at −0.14 GPa (the green curve) also showed small hysteresis, but were offset from the original curve in the other direction. Evidently, the hysteretic part of ρ_{xy} remains at least mostly locked in after the stress is released.

Figure 5(b) shows hysteresis loops with backgrounds subtracted; the background is taken as a quadratic function of $\mu_0 H$, obtained independently at each stress. Each hysteresis loop is recorded following this procedure: (a) under applied stress, B is ramped from 0 to +12 T, and then back to 0; (b) the stress is then released, to measure the Hall effect at zero applied stress; (c) the stress is re-applied, and B ramped from 0 to −12 T, then to 0; (d) the stress is released again and the Hall effect re-measured. The 0 GPa readings are indicated by large squares: it is apparent that releasing the stress causes essentially no change in ρ_{xy} . Hysteresis loops for samples 2 and 3, though without the ramps back to 0 GPa, are shown in figure 5(c).

The anomalous Hall conductivity $\sigma_{\text{AHE}} = -\rho_{\text{AHE}}/\rho^2$ for samples 1 and 2 is shown in figure 6(a). ρ_{AHE} at each stress is taken as $\frac{1}{2}[\rho_{xy}^+(H=0) - \rho_{xy}^-(H=0)]$, where ρ_{xy}^{\pm} is the Hall resistivity after application of $\mu_0 H = \pm 12$ T for sample 1 and ± 10 T for sample 2. ρ_{xx} is taken from sample 4, where the contact configuration permitted accurate measurement; see figure 2. The grey squares in figure 6(a) show σ_{xy} derived from data taken while holding the applied stress, and the red lines after the stress was ramped back to zero. There is no significant difference between them, which shows that any stress-induced ferromagnetic moment contributes negligibly to the AHE.





After a year-long pause, we attempted to achieve saturation of the AHE in sample 1 by driving it to higher compression. These data points are indicated by the X's in figure 6(a). Their position is shifted by hand along the stress axis to match the earlier data set, compensating for relaxation in the mounting epoxy that occurred during the long pause. These data make clear that within the limits of our maximum field (12 T) and the elastic limit of the samples (~ 0.2 GPa) clear saturation could not be achieved, and it is not clear how much higher field and/or stress would be required. The coercive field for strained bulk Mn_3Pt is evidently far higher than that observed in the thin film study, where it was ~ 0.1 T [26]. Disorder and/or interface effects may have suppressed the coercive field in the thin films.

Separately, we note that in [26] the intrinsic AHE was calculated to have a strain dependence. According to this calculation, at the largest stress that we reached the anomalous Hall conductivity would be 4% larger than at zero stress. Such a change would be at the edge of our present sensitivity.

Figure 6(b) shows σ_{AHE} of sample 1 at various temperatures, after training the magnetic structure at 300 K with $\sigma = -0.14$ GPa and $\mu_0 H = \pm 12$ T. σ_{xy} increases steadily with cooling, as was observed with Mn_3Ge [12].


We now show, in figure 7, stress-induced hysteresis for sample 4, which was the one with a transverse configuration: compression along [100], $\mathbf{H} \parallel [001]$. As for sample 1, for sample 4 there was discernible though small hysteresis at zero applied stress. Measurements at three different temperatures (100, 200, and 298 K), shown in figure 7(c), reveal a consistent effect of the applied stress: σ_{AHE} decreases under compression, a change of the opposite sign to that observed when $\sigma \parallel [001]$. However, the quantitative effect is much smaller than for $\sigma \parallel [001]$.

4. Discussion and conclusion

We have shown that the AHE of Mn_3Pt can be trained by simultaneous application of uniaxial stress and field. In other words, uniaxial stress reduces the coercive field for reorientation of the antiferromagnetic domains. Stress that is longitudinal with respect to the field is more effective than transverse stress. In this section we discuss three possible mechanisms by which uniaxial stress might reduce the coercive field. (a) Piezomagnetism due to out-of-plane rotation of the spins (b) piezomagnetism due to in-plane rotation of the spins; and (c) approach to an alternative magnetic ground state.

Piezomagnetism is given by $M_i = \sum_{j,k} \Lambda_{ijk} \sigma_{jk}$, where \mathbf{M} is the induced magnetic moment, σ is stress, and Λ_{ijk} is the piezomagnetic tensor. For the magnetic space group of Mn_3Pt , $R\bar{3}m'$, Λ_{zzz} and Λ_{zxx} are both nonzero, though with different coefficients. This means that both z -axis and x -axis uniaxial stress can induce a z -axis magnetic moment. Due to concerns about plastic deformation we did not attempt to measure the piezomagnetism of Mn_3Pt . In the epitaxial thin film study of [26], a net magnetic moment of $4.6 \text{ m}\mu_{\text{B}}/\text{Mn}$ was obtained for a 20 nm-thick film with $c/a = 0.990$. For bulk samples, that ratio of c/a would be obtained under a uniaxial stress of $\sigma \approx -0.8$ GPa,⁵ indicating a piezomagnetic coefficient of $\approx 6 \text{ (m}\mu_{\text{B}}/\text{Mn)/GPa}$. At our largest stress of $\sigma \sim -0.2$ GPa, a piezomagnetic moment of $1.2 \text{ m}\mu_{\text{B}}/\text{Mn}$ would be obtained, well above

⁵ The bulk modulus of Mn_3Pt is 115 ± 8 GPa [39], and the Poisson's ratio is 0.35 [26], which together yield a Young's modulus of 106 ± 7 GPa.



our upper limit for the spontaneous magnetisation in unstressed Mn_3Pt . For comparison, $8 \text{ (m}\mu_{\text{B}}/\text{Mn)}/\text{GPa}$ has been measured for in-plane stress applied to Mn_3Sn [30], and $\sim 100 \text{ (m}\mu_{\text{B}}/\text{Mn)}/\text{GPa}$ has been reported for Mn_3NiN [38].

In the triangular state at $T < T_t$, there are eight equivalent domain types. There are four possible spin planes: (111), ($\bar{1}\bar{1}1$), ($\bar{1}1\bar{1}$), and ($1\bar{1}\bar{1}$), and for each there are two domain types, related by time reversal. Following [7], these can be classed as A-phases, where the spins point outward with respect to the triangle that is higher along [001], and B-phases, where they point inward—see figure 1 for an illustration. In the experimental geometry here, where our Hall effect measurements probe effective fields parallel to [001], the AHE from A and B phases will be opposite.

We discuss now the first of the possible mechanisms listed above: out-of-plane spin rotation. For each of the possible spin planes, the angle between the axis of the spin plane (line perpendicular to the spin plane) and the [100] and [001] directions is the same. This means that the out-of-plane rotation induced by [001] and [100] uniaxial stress should be nearly the same. Therefore, this form of piezomagnetism would not account for the differing effects of longitudinal versus transverse stress.

The second possible method, in-plane spin rotation, could explain the difference between longitudinal and transverse stress. The black arrows in figure 1 indicate the expected spin rotation under compression along [001] for the A and B phases, under an assumption of in-plane spin rotation. Spin 1 does not rotate because there is no symmetry breaking between clockwise and counter-clockwise rotation. Spins 2 and 3 rotate away from spin 1 because the bond length to spin 1 is reduced. That the magnetic interaction energy increases with reduced bond length is shown by the fact that T_N under strong hydrostatic compression, where the collinear phase is suppressed and the transition at T_N is directly into the triangular phase, increases with compression [39]. Measurements of spin waves show in addition that nearest-neighbour interaction is dominant [40]. For the A phase, the resulting net moment points along $[11\bar{2}]$. Compression along [100], on the other hand, would cause spins 1 and 3 to rotate, resulting in a net moment for the A phase along $[\bar{1}11]$. Its projection along [001] is opposite to that induced by [001] compression, and half as large. The same will be true for the other possible spin planes. Therefore, for a given field along [001], opposite domain types—A versus B—should be selected by longitudinal versus transverse stress, with transverse stress being less effective. We note that orbital polarisation could add comparably to, and even reverse, the net moment from spin rotation [41, 42], but this anisotropy remains. Thus, piezomagnetism from in-plane spin rotation could explain both the opposite sign and differing magnitudes of the AHE induced by [001] and [100] uniaxial stress, for $\mathbf{H} \parallel [001]$.

The third possible mechanism, approach to an alternative magnetic ground state, is one for which we cannot provide specific evidence, but which is nevertheless possible. Stress along $\langle 100 \rangle$ directions is not aligned with the principal axes of the magnetic order or the local easy axes of the Mn spins, making it likely that the applied stress will eventually favour an alternative ground state. In other magnetic systems, stresses well below 1 GPa have been observed to qualitatively change the magnetic structure [43, 44]. There is evidence for closely-spaced ground states in Mn-based systems. In Mn_3GaN , a state where the spins are rotated by 90° with respect to the Mn_3Pt structure may be the ground state [45–47], and may be close to the ground state in Mn_3Pt [48]. In Mn_3Ge and Mn_3Ga there is a strong susceptibility for rotation of the spins

out of the plane [49, 50]. Therefore, it is possible that the coercive field of Mn_3Pt weakens under uniaxial stress because magnetic anisotropy weakens as an alternative magnetic ground state is approached.

As in the thin film study, the AHE observed here is of the same order of magnitude as predicted theoretically [26, 31]. Without demonstration of saturation of the magnetic domains, we cannot offer detailed comments on the magnitude of ρ_{AHE} .

In conclusion, we have shown that uniaxial stress reduces the coercive field for training the magnetic structure of Mn_3Pt , allowing experimental observation, for the first time, of the AHE in bulk samples of a cubic member of the Mn_3X family. The AHE induced by stress and field remains locked in after the stress is released, which shows that the effect of any stress-induced ferromagnetic moment on the Hall effect is negligible. Longitudinal stress reduces the coercive field faster than transverse stress, an observation suggesting that in-plane spin rotation is the dominant response to the applied stress. This hypothesis is not the only possibility, and so should be tested through direct observation of the piezomagnetism. Saturation of the AHE may prove possible through combinations of stress and field directions not probed here, allowing precise comparison with calculations on single crystals, and we therefore encourage further experimentation.

Data availability statement

The data that support the findings of this study are available upon reasonable request from the authors.

Acknowledgments

We thank Peter Milde, Yan Sun, and Binghai Yan for useful discussions. We thank in addition Tomoya Higo and Satoru Nakatsuji for critical readings of our manuscript, and Hua Chen for assistance with the piezomagnetic tensor. We also thank Renate Hempel-Weber and Ulrike Ließ for technical assistance. We acknowledge the financial support of the Max Planck Society. BZ, CF, APM, and CWH acknowledge in addition financial support from the Deutsche Forschungsgemeinschaft through SFB 1143 (Project ID 247310070). KM and CF acknowledge financial support from the European Research Council (ERC), Advanced Grant No. 742068 ‘TOPMAT’; European Union’s Horizon 2020 research and innovation program (Grant Nos. 824123 and 766566). Additionally, KM acknowledges funding support from Max Planck Society under Max Planck-India partner group project and the Board of Research in Nuclear Sciences (58/20/03/2021- BRNS, DAE-YSRA), Department of Atomic Energy (DAE), Government of India. H M L N acknowledges support from the Alexander von Humboldt Foundation through a Research Fellowship for Postdoctoral Researchers. Research in Dresden benefits from the environment provided by the DFG Cluster of Excellence ct.qmat (EXC 2147, project ID 390858940).

ORCID iDs

Belén E Zuniga-Cespedes  <https://orcid.org/0000-0001-5969-8448>

Po-Ya Yang  <https://orcid.org/0000-0003-0726-7763>

Michael Nicklas  <https://orcid.org/0000-0001-6272-2162>

Clifford W Hicks  <https://orcid.org/0000-0002-1736-1406>

References

- [1] Pugh E M and Lippert T W 1932 Hall e.m.f. and intensity of magnetization *Phys. Rev.* **42** 709
- [2] Fang Z, Nagaosa N, Takahashi K S, Asamitsu A, Mathieu R, Ogasawara T, Yamada H, Kawasaki M, Tokura Y and Terakura K 2003 The anomalous Hall effect and magnetic monopoles in momentum space *Science* **302** 92
- [3] Karplus R and Luttinger J M 1954 Hall effect in ferromagnetics *Phys. Rev.* **95** 1154
- [4] Nagaosa N, Sinova J, Onoda S, MacDonald A H and Ong N P 2010 Anomalous Hall effect *Rev. Mod. Phys.* **82** 1539
- [5] Shindou R and Nagaosa N 2001 Orbital ferromagnetism and anomalous Hall effect in antiferromagnets on the distorted fcc lattice *Phys. Rev. Lett.* **87** 116801
- [6] Machida Y, Nakatsuji S, Onoda S, Tayama T and Sakakibara T 2010 Time-reversal symmetry breaking and spontaneous Hall effect without magnetic dipole order *Nature* **463** 210
- [7] Chen H, Niu Q and MacDonald A H 2014 Anomalous Hall effect arising from noncollinear antiferromagnetism *Phys. Rev. Lett.* **112** 017205
- [8] Kübler J and Felser C 2014 Non-collinear antiferromagnets and the anomalous Hall effect *Europhys. Lett.* **108** 67001
- [9] Nakatsuji S, Kiyohara N and Higo T 2015 Large anomalous Hall effect in a non-collinear antiferromagnet at room temperature *Nature* **527** 212
- [10] Li X *et al* 2019 Chiral domain walls of Mn_3Sn and their memory *Nature Commun.* **10** 3021
- [11] Nayak A K *et al* 2016 Large anomalous Hall effect driven by a nonvanishing Berry curvature in the noncollinear antiferromagnet Mn_3Ge *Sci. Adv.* **2** e1501870
- [12] Kiyohara N, Tomita T and Nakatsuji S 2016 Giant anomalous Hall effect in the chiral antiferromagnet Mn_3Ge *Phys. Rev. Appl.* **5** 064009

- [13] Liu Z H, Zhang Y J, Liu G D, Ding B, Liu E K, Jafri H M, Hou Z P, Wang W H, Ma X Q and Wu G H 2017 Transition from anomalous Hall effect to topological Hall effect in hexagonal non-collinear magnet Mn_3Ga *Sci. Rep.* **7** 515
- [14] Otani Y and Higo T 2021 Domain structure and domain wall dynamics in topological chiral antiferromagnets from the viewpoint of magnetic octupole *Appl. Phys. Lett.* **118** 040501
- [15] Nakatsuji S and Arita R 2022 Topological magnets: functions based on berry phase and multipoles *Annu. Rev. Condens. Matter Phys.* **13** 119
- [16] Nagamiya T, Tomiyoshi S and Yamaguchi Y 1982 Triangular spin configuration and weak ferromagnetism of Mn_3Sn and Mn_3Ge *Solid State Commun.* **42** 385
- [17] Szunyogh L, Lazarovits B, Udvardi L, Jackson J and Nowak U 2009 Giant magnetic anisotropy of the bulk antiferromagnets $IrMn$ and $IrMn_3$ from first principles *Phys. Rev. B* **79** 020403
- [18] Duan T F, Ren W J, Liu W L, Li S J, Liu W and Zhang Z D 2015 Magnetic anisotropy of single-crystalline Mn_3Sn in triangular and helix-phase states *Appl. Phys. Lett.* **107** 082403
- [19] Kota Y, Tsuchiura H and Sakuma A 2008 Ab-initio study on the magnetic structures in the ordered Mn_3Pt alloy *IEEE Trans. Magn.* **44** 3131
- [20] Umetsu R Y, Sakuma A and Fukamichi K 2006 Magnetic anisotropy energy of antiferromagnetic $L1_0$ -type equiatomic Mn alloys *Appl. Phys. Lett.* **89** 052504
- [21] Tsunoda M, Imakita K-I, Naka M and Takahashi M 2006 $L1_2$ phase formation and giant exchange anisotropy in $Mn_3Ir/Co-Fe$ bilayers *J. Magn. Magn. Mater.* **304** 55
- [22] Tsunoda M, Naka M, Imakita K-I, Yoshitaki S-I and Takahashi M 2006 Exchange anisotropy of $L1_2-Mn_3X$ ($X = Ir, Rh, Ru$)/Co-Fe bilayers *IEEE Trans. Magn.* **42** 2999
- [23] Aley N P, Vallejo-Fernandez G, Kroeger R, Lafferty B, Agnew J, Lu Y and O'Grady K 2008 Texture effects in $IrMn/CoFe$ exchange bias systems *IEEE Trans. Magn.* **44** 2820
- [24] Kohn A, Kovács A, Fan R, McIntyre G, Ward R and Goff J 2013 The antiferromagnetic structures of $IrMn_3$ and their influence on exchange-bias *Sci. Rep.* **3** 1
- [25] LeBlanc M D, Plumer M L, Whitehead J P and Southern B W 2013 Monte Carlo simulations of the fcc kagome lattice: competition between triangular frustration and cubic anisotropy *Phys. Rev. B* **88** 094406
- [26] Liu Z Q et al 2018 Electrical switching of the topological anomalous Hall effect in a non-collinear antiferromagnet above room temperature *Nat. Electron.* **1** 172
- [27] Mukherjee J, Suraj T S, Basumatary H, Sethupathi K and Raman K V 2021 Sign reversal of anomalous Hall conductivity and magnetoresistance in cubic noncollinear antiferromagnet Mn_3Pt thin films *Phys. Rev. Mater.* **5** 014201
- [28] Iwaki H, Kimata M, Ikebuchi T, Kobayashi Y, Oda K, Shiota Y, Ono T and Moriyama T 2020 Large anomalous hall effect in $L1_2$ -ordered antiferromagnetic Mn_3Ir thin films *Appl. Phys. Lett.* **116** 022408
- [29] Boldrin D et al 2019 Anomalous Hall effect in noncollinear antiferromagnetic Mn_3NiN thin films *Phys. Rev. Mat.* **3** 094409
- [30] Ikhlās M, Dasgupta S, Theuss F, Higo T, Kittaka S, Ramshaw B J, Tchernyshyov O, Hicks C W and Nakatsuji S 2022 Piezomagnetic switching of the anomalous Hall effect in an antiferromagnet at room temperature *Nat. Phys.* **18** 1086–93
- [31] Zhang Y, Sun Y, Yang H, Železný J, Parkin S P, Felser C and Yan B 2017 Strong anisotropy anomalous Hall effect and spin Hall effect in the chiral antiferromagnetic compounds Mn_3X ($X = Ge, Sn, Ga, Ir, Rh$ and Pt) *Phys. Rev. B* **95** 075128
- [32] Li G et al 2019 Optimization of catalytic active sites in non-collinear antiferromagnetic Mn_3Pt bulk single-crystal *Mater. Today Phys.* **10** 100137
- [33] Barber M E, Steppke A, Mackenzie A P and Hicks C W 2019 Piezoelectric-based uniaxial pressure cell with integrated force and displacement sensors *Rev. Sci. Instr.* **90** 023904
- [34] Ikhlās M, Shirer K R, Yang P-Y, Nakatsuji S and Hicks C W 2020 A tunable stress dilatometer and measurement of the thermal expansion under uniaxial stress of Mn_3Sn *Appl. Phys. Lett.* **117** 233502
- [35] Krén E, Kádár G, Pál L, Sólyom J and Szabó P 1966 Magnetic structures and magnetic transformations in ordered $Mn_3(Rh, Pt)$ alloys *Phys. Lett.* **20** 331
- [36] Krén E, Kádár G, Pál L and Szabó P 1967 Investigation of the first-order magnetic transformation in Mn_3Pt *J. Appl. Phys.* **38** 1265
- [37] Krén E, Kádár G, Pál L, Sólyom J, Szabó P and Tarnóczy T 1968 Magnetic structures and exchange interactions in the Mn-Pt system *Phys. Rev.* **171** 574
- [38] Boldrin D et al 2018 Giant piezomagnetism in Mn_3NiN *ACS Appl. Mater. Interfaces* **10** 18863
- [39] Yasui H, Kaneko T, Yoshida H, Abe S, Kamigaki K and Mori N 1987 Pressure dependence of magnetic transition temperatures and lattice parameter in an antiferromagnetic ordered alloy Mn_3Pt *J. Phys. Soc. Japan* **56** 4532
- [40] Ikeda T and Tsunoda Y 2003 Spin fluctuations in an octahedral antiferromagnet Mn_3Pt alloy *J. Phys. Soc. Japan* **72** 2614
- [41] Sandratskii L M and Kübler J 1996 Role of orbital polarization in weak ferromagnetism *Phys. Rev. Lett.* **76** 4963
- [42] Chen H, Wang T-C, Xiao D, Guo G-Y, Niu Q and MacDonald A H 2020 Manipulating anomalous Hall antiferromagnets with magnetic fields *Phys. Rev. B* **101** 104418
- [43] Park J, Sakai K, Erten O, Mackenzie A P and Hicks C W 2018 Effect of applied orthorhombic lattice distortion on the antiferromagnetic phase of $CeAuSb_2$ *Phys. Rev. B* **97** 024411
- [44] Sun D, Sokolov D A, Waite R, Khim S, Manuel P, Orlandi F, Khalyavin D D, Mackenzie A P and Hicks C W 2021 Heisenberg spins on an anisotropic triangular lattice: $PdCrO_2$ under uniaxial stress *New J. Phys.* **23** 123050
- [45] Lukashov P, Sabirianov R F and Belashchenko K 2008 Theory of the piezomagnetic effect in Mn-based antiperovskites *Phys. Rev. B* **78** 184414
- [46] Zemen J, Gercsi Z and Sandeman K G 2017 Piezomagnetism as a counterpart of the magnetovolume effect in magnetically frustrated Mn-based antiperovskite nitrides *Phys. Rev. B* **96** 024451
- [47] Samathrakris I and Zhang H 2020 Tailoring the anomalous Hall effect in the noncollinear antiperovskite Mn_3GaN *Phys. Rev. B* **101** 214423
- [48] Bai H et al 2021 Control of spin-orbit torques through magnetic symmetry in differently oriented noncollinear antiferromagnetic Mn_3Pt *Phys. Rev. B* **104** 104401
- [49] Sukhanov A S et al 2018 Gradual pressure-induced change in the magnetic structure of the noncollinear antiferromagnet Mn_3Ge *Phys. Rev. B* **97** 214402
- [50] Song L, Ding B, Li H, Lv S, Yao Y, Zhao D, He J and Wang W 2021 Observation of structural distortion and topological Hall effect in noncollinear antiferromagnetic hexagonal Mn_3Ga magnets *Appl. Phys. Lett.* **119** 152405